

PERMEABLE PAVEMENT SYSTEM

STANDARD TEST METHOD BELOW IS ASTM C1781 FOR SURFACE INFILTRATION RATE OF PERMEABLE UNIT PAVEMENT SYSTEMS.

STONE TYPE	STONE FINISH	PATTERN	STONE THICKNESS	ADDITIONAL INFORMATION	INFILTRATION RATE INCH PER HOUR
MARBLE	SANDBLASTED	16"x24", 12"x24" RUNNING BOND PATTERN	1 3/16"	3/8" JOINT	489.5
MARBLE	SANDBLASTED	FRENCH PATTERN	1 3/16"	TIGHT JOINT	378.9
TRAVERTINE	ANTIQUED	16"x24", 12"x24" RUNNING BOND	1 3/16"	1/4" JOINT	719.2
MARBLE	ANTIQUED	FRENCH PATTERN	1 3/16"	TIGHT JOINT	719.2
GRANITE	WATER BLASTED	4"x4" RUNNING BOND	2.25"	1/4" JOINT	881.0
MARBLE	SANDBLASTED	FRENCH PATTERN	1 3/16"	1/4" JOINT	587.4
TRAVERTINE	ANTIQUED	24"x24", 16"x16" 12"x12", STACKED BOND PATTERN	1 3/16"	3/8" JOINT	597.3
MARBLE	ANTIQUED	6"x12" HERRINGBONE PATTERN	2.25"	1/4" JOINT	451.8
TRAVERTINE	RECLAIMED	GATEWAY PATTERN™	2.25"	1/4" JOINT	503.5
MARBLE	SANDBLASTED	24"x24", 16"x16" 12"x12", STACKED BOND PATTERN	1 3/16"	1/4" JOINT	597.3

DISCLAIMER

Marmiro Stones, Inc. has no control over the buyer's selection or use of any stone. Prior to using or permitting the use of our products, the buyer must determine the suitability of the products for the intended use and assumes all risk and liability whatsoever in connection therewith. The buyer must also determine the slip resistance suitability and maintainability as Marmiro Stones, Inc. is not responsible for any losses or damages sustained by the buyer, or any other person, as a result of improper installation or misapplication of our products. Please refer to the ASTM standards for more specific information concerning stone or paver specifications. Marmiro Stones, Inc. and its agents and employees are held harmless against any loss, damage, claim, suit, liability, judgement, or expense arising out of, or in connection with, any injury, damage, or loss to any property, or violation of any applicable laws or regulations resulting from, or in connection with, the sale, transportation, installation, or use of our products by the buyer.