



Product: Afyon Cloud®

Type: Marble

Origin: Iscehisar, Turkey since 1971

Color: A blend of light and dark grays to match the puffy

clouds in the sky.

Sandblasted Finished: A lightly textured surface with modern, straight edges.

Sandblasted Density

164.2 lbs/ft3

TECHNICAL SPECIFICATIONS

Compressive Strength ASTM - C170

Sample	Antiqued	Sandblasted
Afyon Cloud® Marble	10,968 psi	10,208 psi
Flexural Strength ASTM - C880		
Sample	Antiqued	Sandblasted
Afyon Cloud® Marble	N/A	1,308 psi
Co-Efficient of Friction ASTM - C1028 (Ar	ntiqued Stones)	
Sample	Antiqued Dry	Antiqued Wet
Afyon Cloud® Marble	0.74	0.83
Co-Efficient of Friction ASTM - C1028 (Sa	andblasted Stones)	
Sample	Sandblasted Dry	Sandblasted Wet
Afyon Cloud® Marble	0.97	1.04
Freeze and Thaw ASTM - C666		
Sample	Results	Notes
Afyon Cloud® Marble	Pass	No cracks or deformations noted.
Water Absorption ASTM - C97		
Sample	Antiqued Water Absorption %	Sandblasted Water Absorption %
Afyon Cloud® Marble	0.17	0.16
Density ASTM - C97		

DISCLAIMER

Afyon Cloud® Marble

Sample

Marmiro Stones, Inc. has no control over the buyer's selection or use of any stone. Prior to using or permitting the use of our products, the buyer must determine the suitability of the products for the intended use and assumes all risk and liability whatsoever in connection therewith. The buyer must also determine the slip resistance suitability and maintainability as Marmiro Stones, Inc. is not responsible for any losses or damages sustained by the buyer, or any other person, as a result of improper installation or misapplication of our products. Please refer to the ASTM standards for more specific information concerning stone or paver specifications. Marmiro Stones, Inc. and its agents and employees are held harmless against any loss, damage, claim, suit, liability, judgement, or expense arising out of, or in connection with, any injury, damage, or loss to any property, or violation of any applicable laws or regulations resulting from, or in connection with, the sale, transportation, installation, or use of our products by the buyer.

Antiqued Density

162.4 lbs/ft3

^{*} Permeable pavement system test results are available on our website under resources or you can email marketing@marmiro.com. for more details.