



Product: Crema Eda®

Type: Marble

Origin: Sivrihisar, Turkey since 1989

Color: A neutral, creamy beige to match any color palette.

Antiqued Finished: Aged look with a smooth surface and tumbled edges.

* Permeable pavement system test results are available on our website under resources or you can email marketing@marmiro.com. for more details.

167.4 lbs/ft3

TECHNICAL SPECIFICATIONS

Compressive Strength ASTM - C170

Sample	Antiqued	Sandblasted
Crema Eda® Marble	13,453 psi	12,080 psi
Flexural Strength ASTM - C880		
Sample	Antiqued	Sandblasted
Crema Eda® Marble	N/A	1,284 psi
Co-Efficient of Friction ASTM - C1028 (Ant	iqued Stones)	
Sample	Antiqued Dry	Antiqued Wet
Crema Eda® Marble	0.74	0.87
Co-Efficient of Friction ASTM - C1028 (San	dblasted Stones)	
Sample	Sandblasted Dry	Sandblasted Wet
Crema Eda® Marble	0.91	0.87
Freeze and Thaw ASTM - C666		
Sample	Results	Notes
Crema Eda® Marble	Pass	No cracks or deformations noted.
Water Absorption ASTM - C97	Antiqued Weter Absorption V	Conditionated Water Absorption V
Sample	Antiqued Water Absorption %	Sandblasted Water Absorption %
Crema Eda® Marble	0.17	0.19
Density ASTM - C97 Sample	Antiqued Density	Sandblasted Density

DISCLAIMER

Crema Eda® Marble

Marmiro Stones, Inc. has no control over the buyer's selection or use of any stone. Prior to using or permitting the use of our products, the buyer must determine the suitability of the products for the intended use and assumes all risk and liability whatsoever in connection therewith. The buyer must also determine the slip resistance suitability and maintainability as Marmiro Stones, Inc. is not responsible for any losses or damages sustained by the buyer, or any other person, as a result of improper installation or misapplication of our products. Please refer to the ASTM standards for more specific information concerning stone or paver specifications. Marmiro Stones, Inc. and its agents and employees are held harmless against any loss, damage, claim, suit, liability, judgement, or expense arising out of, or in connection with, any injury, damage, or loss to any property, or violation of any applicable laws or regulations resulting from, or in connection with, the sale, transportation, installation, or use of our products by the buyer.

168.5 lbs/ft3