



Product: Crema Eda® Rosa

Type: Marble

Origin: Sivrihisar, Turkey since 1989

Color: A creamy beige with wisps of red veins.

**Sandblasted Finished:** A lightly textured surface with modern, straight edges.

## TECHNICAL SPECIFICATIONS

## **Compressive Strength ASTM - C170**

Sample	Antiqued	Sandblasted
Crema Eda® Rosa Marble	12,675 psi	13,434 psi
Flexural Strength ASTM - C880		
Sample	Antiqued	Sandblasted
Crema Eda® Rosa Marble	N/A	1,466 psi
Co-Efficient of Friction ASTM - C1028 (Antique and the second s	ued Stones)	
Sample	Antiqued Dry	Antiqued Wet
Crema Eda® Rosa Marble	0.74	0.87
Co-Efficient of Friction ASTM - C1028 (Sandl	plasted Stones)	
Sample	Sandblasted Dry	Sandblasted Wet
Crema Eda® Rosa Marble	0.89	0.95
Freeze and Thaw ASTM - C666		
Sample	Results	Notes
Crema Eda® Rosa Marble	Pass	No cracks or deformations noted.
Water Absorption ASTM - C97 Sample	Antiqued Water Absorption %	Sandblasted Water Absorption %
- Crema Eda® Rosa Marble	0.17	0.16
Density ASTM - C97 Sample	Antiqued Density	Sandblasted Density
Crema Eda® Rosa Marble	0.17	0.16

## DISCLAIMER

Marmiro Stones, Inc. has no control over the buyer's selection or use of any stone. Prior to using or permitting the use of our products, the buyer must determine the suitability of the products for the intended use and assumes all risk and liability whatsoever in connection therewith. The buyer must also determine the slip resistance suitability and maintainability as Marmiro Stones, Inc. is not responsible for any losses or damages sustained by the buyer, or any other person, as a result of improper installation or misapplication of our products. Please refer to the ASTM standards for more specific information concerning stone or paver specifications. Marmiro Stones, Inc. and its agents and employees are held harmless against any loss, damage, claim, suit, liability, judgement, or expense arising out of, or in connection with, any injury, damage, or loss to any property, or violation of any applicable laws or regulations resulting from, or in connection with, the sale, transportation, installation, or use of our products by the buyer.