



Product: Deep Blue®

Type: Marble

Origin: Iscehisar, Turkey since 1971

Color: A deep bluish gray with unique pattern

characteristics.

Antiqued Finished: Aged look with a smooth surface and tumbled edges.

* Permeable pavement system test results are available on our website under resources or you can email marketing@marmiro.com. for more details.

TECHNICAL SPECIFICATIONS

Compressive Strength ASTM - C170

12,082 psi Antiqued	11,929 psi Sandblasted
•	Sandblasted
•	Sandblasted
N/A	
IV/A	1,878 psi
Antiqued Dry	Antiqued Wet
0.77	0.87
s)	
Sandblasted Dry	Sandblasted Wet
0.99	0.87
Results	Notes
Pass	No cracks or deformations noted.
ued Water Absorption %	Sandblasted Water Absorption %
0.17	0.18
Antiqued Density	Sandblasted Density
163.8 lbs/ft³	167.4 lbs/ft³
	0.77 S) Sandblasted Dry 0.99 Results Pass Jued Water Absorption % 0.17 Antiqued Density

DISCLAIMER

Marmiro Stones, Inc. has no control over the buyer's selection or use of any stone. Prior to using or permitting the use of our products, the buyer must determine the suitability of the products for the intended use and assumes all risk and liability whatsoever in connection therewith. The buyer must also determine the slip resistance suitability and maintainability as Marmiro Stones, Inc. is not responsible for any losses or damages sustained by the buyer, or any other person, as a result of improper installation or misapplication of our products. Please refer to the ASTM standards for more specific information concerning stone or paver specifications. Marmiro Stones, Inc. and its agents and employees are held harmless against any loss, damage, claim, suit, liability, judgement, or expense arising out of, or in connection with, any injury, damage, or loss to any property, or violation of any applicable laws or regulations resulting from, or in connection with, the sale, transportation, installation, or use of our products by the buyer.