



Product: Terra Antiqued Straight Edge Coping

Type: Travertine

Origin: Denizli, Turkey since 2005

Color: A rustic variation of light and dark browns and tans.

Antiqued Finished: Aged look with a smooth surface and tumbled edges.

** Permeable pavement system test results are available on our website under resources or you can email marketing@marmiro.com for more details.*

TECHNICAL SPECIFICATIONS

Compressive Strength ASTM - C170

| Sample | Antiqued | Sandblasted |
|------------------|-----------|-------------|
| Terra Travertine | 8,645 psi | N/A |

Flexural Strength ASTM - C880

| Sample | Antiqued | Sandblasted |
|------------------|-----------|-------------|
| Terra Travertine | 1,878 psi | N/A |

Co-Efficient of Friction ASTM - C1028 (Antiqued Stones)

| Sample | Antiqued Dry | Antiqued Wet |
|------------------|--------------|--------------|
| Terra Travertine | 0.70 | 0.89 |

Co-Efficient of Friction ASTM - C1028 (Sandblasted Stones)

| Sample | Sandblasted Dry | Sandblasted Wet |
|------------------|-----------------|-----------------|
| Terra Travertine | N/A | N/A |

Freeze and Thaw ASTM - C666

| Sample | Results | Notes |
|------------------|---------|----------------------------------|
| Terra Travertine | Pass | No cracks or deformations noted. |

Water Absorption ASTM - C97

| Sample | Antiqued Water Absorption % | Sandblasted Water Absorption % |
|------------------|-----------------------------|--------------------------------|
| Terra Travertine | 1.98 | N/A |

Density ASTM - C97

| Sample | Antiqued Density | Sandblasted Density |
|------------------|---------------------------|---------------------|
| Terra Travertine | 153.1 lbs/ft ³ | N/A |

DISCLAIMER

Marmiro Stones, Inc. has no control over the buyer's selection or use of any stone. Prior to using or permitting the use of our products, the buyer must determine the suitability of the products for the intended use and assumes all risk and liability whatsoever in connection therewith. The buyer must also determine the slip resistance suitability and maintainability as Marmiro Stones, Inc. is not responsible for any losses or damages sustained by the buyer, or any other person, as a result of improper installation or misapplication of our products. Please refer to the ASTM standards for more specific information concerning stone or paver specifications. Marmiro Stones, Inc. and its agents and employees are held harmless against any loss, damage, claim, suit, liability, judgement, or expense arising out of, or in connection with, any injury, damage, or loss to any property, or violation of any applicable laws or regulations resulting from, or in connection with, the sale, transportation, installation, or use of our products by the buyer.