



Product: Marmiro Bluestone

Type: Sandstone

Origin: Asia

Color: Charcoal grey stone with a wavy texture throughout

Flamed Finish: When an intense flame is fired at the stone, causing the surface to burst and become rough.

** Permeable pavement system test results are available on our website under resources or you can email marketing@marmiro.com. for more details.*

TECHNICAL SPECIFICATIONS

Compressive Strength ASTM - C170

Sample	Antiqued	Sandblasted / Flamed
Marmiro Bluestone	N/A	14,133 psi

Flexural Strength ASTM - C880

Sample	Antiqued	Sandblasted / Flamed
Marmiro Bluestone	N/A	1,785 psi

Freeze and Thaw ASTM - C666

Sample	Results	Notes
Marmiro Bluestone	Pass	No cracks or deformations noted.

Water Absorption ASTM - C97

Sample	Antiqued Water Absorption %	Sandblasted / Flamed Water Absorption %
Marmiro Bluestone	N/A	1.76

Density ASTM - C97

Sample	Antiqued Density	Sandblasted / Flamed Density
Marmiro Bluestone	N/A	160.5 lbs/ft ³

DISCLAIMER

Marmiro Stones, Inc. has no control over the buyer's selection or use of any stone. Prior to using or permitting the use of our products, the buyer must determine the suitability of the products for the intended use and assumes all risk and liability whatsoever in connection therewith. The buyer must also determine the slip resistance suitability and maintainability as Marmiro Stones, Inc. is not responsible for any losses or damages sustained by the buyer, or any other person, as a result of improper installation or misapplication of our products. Please refer to the ASTM standards for more specific information concerning stone or paver specifications. Marmiro Stones, Inc. and its agents and employees are held harmless against any loss, damage, claim, suit, liability, judgement, or expense arising out of, or in connection with, any injury, damage, or loss to any property, or violation of any applicable laws or regulations resulting from, or in connection with, the sale, transportation, installation, or use of our products by the buyer.